

Technical Data Sheet of Applecare A100

Product Description

Applecare A100 is an easy-to-use pigment dispersion system for dispersing the cosmetic inorganic pigment powder and fillers into the oil phase of cosmetic formulation, resulting in a low viscosity, fine, uniform, and high dosage pigment dispersion without the need of pre-surface coating/treatment of the pigments. It is a unique complex, consisted of optimized amount of wetting agents, dispersants, and light cosmetic oils, to perform three critical functions of pigment grinding – wetting, separation of pigment agglomerates, and stabilization of the separated pigment particles.

Legislation

- INCI Polyhydroxystearic acid (and) Lecithin (and) 2-Ethylhexyl Palmitate (and) Isopropyl Myristate (and) Isostearic Acid (and) Polyglyceryl-3 Polyricinoleate
- CAS # 27924998/8002435/110270/29806733/30399849/29894357
- EINECS Exempt/2323072/2037514/2498621/2501780/exempt

General Product Specification

<u>Item</u>	<u>Specification</u>
Appearance	Light brown liquid
Odor	Mild characteristic odor
Dry residue (3 g, 3hrs, 110C)	➤ 95%
Viscosity (cP), 20 rpm, 25C	300 – 1100 cP

Toxicity Data

- **Repeated Insult Patch Tests (RIPT):** The test results on 55 subjects: The product was “Dermatologist-tested” and was not associated with skin irritation or allergic contact dermatitis in human subjects.

----- Create Possibilities -----

Last product specification update: Version 2, 2/24/2017 Last document update: 4/21/2017

- **Applecare A100** is non-GMO, free of gluten, phthalate, pesticide, paraben, and chemicals in the California Proposition 65 listing.
- **Applecare A 100** contains less than 1 ppm of total heavy metal, and less than 100 cfu/g of microbe.

Features/Benefits

- A low viscosity liquid, very easy to use in the color formulation development and in the manufacturing of the color products.
- Applecare A100 can not only disperse the hydrophilic (non-surface treated) inorganic pigments (TiO₂, ZnO, Iron oxide, etc) and fillers in the cosmetic oil into a low viscosity and high pigment load (up to 75% by weight) dispersion with common pigment dispersing equipments such as Cowles disperser, homogenizer, or propeller, etc, but also change their surfaces to hydrophobic, improving their water-resistance and longer-lasting benefits.

This unique combination of dispersing and surface-treating benefits make Applecare A100 an essential ingredient in developing the new color control air cushion compact, which is a multi-tasking silky light CC foundation with broad spectrum SPF 50+, complete coverage, anti-aging and deep skin hydration in an easy-to-use sponge package.

- Since it disperses and surface-treats the less expensive non-surface treated pigments at the same time to match up with the performances of the surface-treated pigments, it practically eliminates the need for the expensive surface-treated pigments. Applecare A100 also works well for the surface-treated pigments, whose coating is not perfect.

Applications

Cosmetic and Toiletry:

- Beauty Products: foundation, mascara, lip products, pencils/liners, eye shadow, blush, etc
 - Color control air cushion compact - a low viscosity W/S-O foundation in a sponge package.
- Compressed or baked powder compact: Use as a liquid binder or part of liquid binders
- Sunscreen products with inorganic UV filters.

How to use it?

- Typical dosage is 5% by weight of the non-surface treated pigments, and is 2-3% for the surface-treated pigments.

----- **Create Possibilities** -----

Last product specification update: Version 2, 2/24/2017 Last document update: 4/21/2017

- Processing to make a 70 – 75% pigment dispersion stock: 1). Mix the oil ingredients and the Applecare A-100 in a vessel at room temperature or preferable at > 65° C. 2) Add the pigment blend in 3 portions – 50%, 30%, and 20%, and mix well at > 65° C until homogeneous before the addition of the next portion. And 3) if desired grind the dispersion further with ball mill or 3-roll mill to a finer dispersion.
- In-situ processing: 1) Mix a portion of the liquid oil components and Applecare A-100 together, so that the final pigment % is 40 % – 50%. Do not add the emulsifiers at this step. 2) Grind the pigments into the oil blend with homogenizer to a fine homogeneous dispersion, preferably at > 65° C. 3) you may incorporate the emulsifiers now and move to the next step in the O/W or W/O emulsion preparation.

Packaging

- Product is available in 16 Kg /5 gallon pail.

Storage

Store the product in its original package, sealed tightly, and protect it from exposure to the extreme low temperature. If Applecare A-100 became a solid from the low temperature, simply heat it to 30C to bring it back to a liquid state. When it is stored over a long period of time, cloudiness may appear at the bottom. Light to moderate mixing or stirring will disperse it back into the liquid.

Due to variations in methods, conditions, and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of information or products for the application disclosed. Nothing contained herein is to be considered as permission, recommendation, nor as inducement to practice any patented invention without the permission of the patent owner. Applechem shall not be liable and the User assumes all risk and responsibility for any use or handling of any material beyond Applechem's direct control.

----- ---- **Create Possibilities** -----

Last product specification update: Version 2, 2/24/2017 Last document update: 4/21/2017